

ZERO LINE EDGEBANDING

- Coextruded version -

SETTINGS FOR VIRUTEX EB150 EDGEBANDING MACHINE

General settings for application of ZERO LINE edgeband - coextruded version - with **VIRUTEX EB150 ZERO LINE** edgebanding machine in order to obtain a correct adhesion.

GENERAL SETTINGS

SPEED	4.5m/min.
TEMPERATURE	400-440°C
PRESSURE	0.6 bar

These parameters are only indicative and may require minor modifications.



cantisa
SOCIEDAD ANONIMA

Tel.: +34 961 597 242
www.cantisa.es
cantisa@cantisa.es